

# ShaliJet® Sealing Compound

Coal Tar Sealing Compound



STP Limited

## Description

**ShaliJet® Sealing Compound** is thermoplastic material. It flows in hot condition and settles to a plasto-elastic mass when cold. Being fuel / heat resistant, **ShaliJet® Sealing Compound** is used as sealant in construction of runways. It conforms to IS:1834 Grade B.

## Characteristics

Colour	Black	Coverage, 100 meters of running joint of 25 mm depth, Kgs	
Aviation Fuel / Kerosene Resistance Test, change in Penetration after 7 days immersion in Aviation fuel / kerosene, at 25 °C, 100 g./ 0.1 mm / 5 sec., max.	15	• 12 mm	44
		• 18 mm	66
		• 25 mm	92
		Pour Point, °C, Max	175
		Softening point °C, Min	85
Flow test @ 45 °C %,max	5	Penetration, 25 °C, 0.1 mm, 5 sec.	15 - 50
Change in mass, %, max	1	Extensibility, mm, min	6

## Application

- Runway Joints
- Joints in garages, filling stations and other places of construction joints like in warehouse floors and secondary containment of walls and floors of artificial water ponds.
- Bridge / road joints.

## Advantages

- Fuel spillage resistant.
- Jet exhaust heat resistant.
- Good adhesion to concrete / other surface.
- Low susceptibility to flow during hot weather condition.
- Resistant to sunlight / rain and cyclic temperature changes.
- Anti-corrosive and prevents root growth.
- Resistant to ingress of foreign substance

## Application Methodology

- Remove dust, flakes, oil, grease or other foreign particles by jet or dry air and clean the surface to make it smooth before applying **ShaliJet Sealing Compound**.
- Spray or brush, on the area where **ShaliJet Sealing Compound** is to be applied, ShaliJet Primer evenly throughout the joints and allow it to dry completely. 24 hrs is enough to dry the primer during normal weather condition.
- Cover the joint by plastic film if rain is expected after primer application.
- Cut ShaliJet Sealing Compound drum and heat it to 180 – 210 °C while slowly stirring the material for uniformity. A 26 kg drum will take 2-3 hrs at 190 – 200 °C for complete melting using hand stirrer. Do not overheat as this may cause frothing. If for any reason bubble appears during melting, keep the temperature around 180°C for a longer time with slow manual stirring till the bubble disappears.
- Upon primer drying completely, pour molten **ShaliJet® Sealing Compound** from one side of the joint allowing it to travel through the joint as much as practicable. While pouring, ensure that temperature of material is in the range of 190 - 200 °C.
- During the pouring process, to avoid spillage, place wooden boards on both sides of joint and pour from can with extended spout.

## Health & Safety.

- **ShaliJet Sealing Compound** is inflammable.
- Use goggles, gumboots, nose covers and hand gloves during application
- Clean hands with warm soap water after application

## Packing

Available in 26 kg and 260 kg drum.

## Storage

Keep in cool and dry place under shed away from heat.

---



**STP Limited**  
**Advisory Cell**  
**+91 81302 81114**  
Waterproofers to the Nation

**STP's Businesses**  
Waterproofing & Insulation  
Road Surfacing  
Pipeline Coating  
Repairs & Rehabilitation  
GARA (Grouts & Admixtures)  
Other Powder Products  
Sealant & Additives  
Epoxy Flooring  
Protective / Anti-Corrosive Coating  
Other Products

