

ShaliUrethane LHM

Single Component Elastomeric Modified Polyurethane WP Membrane



STP Limited

Description

ShaliUrethane LHM is a single component modified polyurethane elastomeric liquid membrane for waterproofing treatment. It forms a seamless membrane by reaction with atmospheric moisture. It conforms to ASTM C-898-2009, C-836-2012.

ShaliUrethane LHM is used for horizontal / vertical applications. For horizontal or vertical applications, please use horizontal or vertical grades of **ShaliUrethane LHM** respectively.

Characteristics

Application	Roller/Airless Spray	Colour	Black
Tack free time, hr	8 -10	Final cure time, hr, solid	24 - 36
Solid content, %	> 85 ± 2	Loss of weight, %	15 ± 2
Hardness, Shore A	30 ± 2	Tensile strength, MPa	0.8 ± 0.1
Elongation, %	> 500	Extension after heat aging, mm	6.4 with no cracking
Crack bridging at low temperature at minus 9 °C, mm	Passed over 1.5	Swelling in water	Nil
Service temp, range, °C	- 40 to 70	VOC Content, gm/kg	150 ± 20
Theoretical Coverage Kg/m ² for 1 mm DFT	1.4 *	Chemical stability	Resistant to most mild acids and alkalies
Adhesion to primed concrete, Pull strength MPa	2.5 ± 0.2		

* Maximum depending upon surface condition.

Application

- Tunnels.
- Roof / Terraces.
- Terrace garden.
- Podium.
- Retaining walls.
- Planter boxes.

Advantages

- Easy to apply
- Easily repairable
- Exhibits good waterproofing character with high elongation property
- Excellent adhesion to concrete
- Resistance to Root Growth

Application Methodology

- Remove all loose gravel, dirt, oil, grease and foreign matter by jet or dry air and clean the surface mechanically or by grinding to make it smooth before application. Ensure that the prepared surface is moisture free.
- Ensure that the minimum slope gradient of 1 in 100 (1 in 80 for large roof slopes) is maintained.
- Stir **ShaliUrethane LHM** by a slow speed mixture (400 – 500 rpm) fitted with a suitable mixing paddle to ensure a homogenous mix. After stirring, wait for the product to settle in order to let entrapped air escape.
- Apply a coat of ShaliPrime PUM @ 8 -10 m² / L and allow it to dry.

- Apply **ShaliUrethane LHM** @ 1.4 kg/m² for 1000 microns DFT (theoretical coverage depending on surface conditions) by roller / airless spray. Preferably, apply the entire quantity in two coats. STP recommends use of ShaliGeoText 50 gsm as reinforcement in between two layers.
- Sprinkle fine sand @ 200 gsm over the final coating when the surface is still tacky, i.e. after around 12 hrs - 15 hrs of the coating of top layer. After complete curing of surface, remove excess/loose sand by brush.
- Apply vertical grade of **ShaliUrethane LHM** on all parapet, projection, etc, In case height of parapet is upto 450 mm, treatment shall be taken up to the top of parapet, otherwise, if height is more than 450 mm, the treatment shall be terminated at a height of 300 mm above the finished roof level.
- Ensure final curing time of 36 hrs before allowing / carrying out any further work.
- Apply ShaliGeoText 250 gsm over fully cured sand sprinkled applied surface. Before laying minimum 50 mm screed protection.
- **Use the material within 4 hours of opening of the container.**
- Skin formation may happen on the top of material during humid condition. In that event, cut skin from the periphery of the container and remove it and then stir it as mentioned above.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapours.
- Wear suitable protective clothing, gloves and eye protection.
- In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of contact with eyes, wash immediately with plenty of clean water and seek medical advice.
- If swallowed seek medical attention immediately. Do not induce vomiting.

Packing

Available in 22 kg packing.

Storage

Store in a cool dry clean place at 4 to 27 °C in original sealed containers. During storage, an easily Removed protective skin of ShaliUrethane LHM may form on top, which does not affect performance of the product.

Shelf Life

6 Months when stored in original sealed container in a cool dry place under shade, away from heat and moisture



STP's Businesses
 Waterproofing & Insulation
 Road Surfacing
 Pipeline Coating
 Repairs & Rehabilitation
 GARA (Grouts & Admixtures)
 Other Powder Products
 Sealant & Additives
 Epoxy Flooring
 Protective / Anti-Corrosive Coating
 Other Products



Visit us at : www.stpltd.com or Email at : info@stpltd.com